

TECHNOMELT SUPRA 7220-21 PS

Known as Technomelt Supra PS 7220-21

October 2013

PRODUCT DESCRIPTION

TECHNOMELT SUPRA 7220-21 PS provides the following product characteristics:

Technology	Synthetic Rubber
Product Type	Hotmelt
Components	One-component
Application	Packaging Industry
Appearance	white

Application Areas

Suitable for palletized cartons, multi packs and bags made from paper or films.

Product Properties

- Due to its film properties it allows clean palletizing. After de-palletizing it is non-sticky.
- High-quality synthetic hotmelt adhesive
- High thermostability
- Good cold flexibility
- Reduced consumption
- Excellent processing properties by nozzle
- Suitable for spin spray application

Technical Data

TECHNOMELT SUPRA 7220-21 PS:

Viscosity, Brookfield, 170 °C, mPa.s	4,000 to 6,000
Open Time	long slightly tacky surface
Softening Point, Ring & Ball, °C	85 to 95

DIRECTIONS OF USE

Preliminary Statement

Prior to application it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Application

Application method:

- nozzle

Recommended working temperature: 150 to 180 °C

TECHNOMELT SUPRA 7220-21 PS is suitable for spot- as well as line- and spray application.

Cleaning

For the cleaning of melting tanks and application systems, we recommend the use of TECHNOMELT CLEANER 1940 or HOTMELT CLEANER Q 1924.

For the cold cleaning of surface soiling on application equipment, conveyor belts or other machine parts, TECHNOMELT CLEANER MELT-O-CLEAN can be applied. TECHNOMELT CLEANER MELT-O-CLEAN is based on natural resources and facilitates manual cleaning even in case of pronounced charring. Before using TECHNOMELT CLEANER MELT-O-CLEAN, its suitability for lacquered and synthetic coated surfaces should be tested.

During use, please follow the safety instructions.

STORAGE

When stored in a dry and cool place in the original unopened containers shelf life is as follows. .

Shelf life:

Shelf-life (in unopened original packaging), months 24

Classification:

Please refer to the corresponding **safety data sheets** for details on:

Hazardous Information

Transport Regulations

Safety Regulations

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1

Henkel AG & Co. KGaA
40191 Düsseldorf, Germany
Phone: +49-211-797-0

Henkel Corporation
Bridgewater, NJ 08807, USA
Phone: +1-908-685-7000

Henkel (China) Co.Ltd.
201203 Shanghai, China
Phone: +86-21-2891-8000

For more information contact us on www.henkel.com